



Mechanical Properties and Microstructure of Biomorphic Silicon Carbide Ceramics Fabricated from Wood Precursors

Ву-

BiblioGov. Paperback. Book Condition: New. This item is printed on demand. Paperback. 28 pages. Dimensions: 9.7in. x 7.4in. x 0.1in.Silicon carbide based, environment friendly, biomorphic ceramics have been fabricated by the pyrolysis and infiltration of natural wood (maple and mahogany) precursors. This technology provides an eco-friendly route to advanced ceramic materials. These biomorphic silicon carbide ceramics have tailorable properties and behave like silicon carbide based materials manufactured by conventional approaches. The elastic moduli and fracture toughness of biomorphic ceramics strongly depend on the properties of starting wood preforms and the degree of molten silicon infiltration. Mechanical properties of silicon carbide ceramics fabricated from maple wood precursors indicate the flexural strengths of 3441-58 MPa at room temperature and 230136 MPa at 1350C. Room temperature fracture toughness of the maple based material is 2.6 - 0.2 MPa(square root of)m while the mahogany precursor derived ceramics show a fracture toughness of 2.0 - 0.2 Mpa(square root of)m. The fracture toughness and the strength increase as the density of final material increases. Fractographic characterization indicates the failure origins to be pores and chipped pockets of silicon. This item ships from La Vergne,TN. Paperback.



Reviews

These kinds of publication is everything and got me to looking ahead of time and much more. it absolutely was writtern extremely completely and valuable. Your way of life period is going to be enhance when you full looking over this ebook.

-- Dr. Lessie Murphy IV

Basically no terms to explain. I have read and so i am certain that i will gonna go through once again once more in the future. I realized this ebook from my dad and i encouraged this book to discover.

-- Forest Little